


内六角平圆头螺钉

代码	类型	螺纹	强度等级	材质	硬度	表面处理		
TAR12	内六角平圆头螺钉	粗牙	8.8	10B21	—	发黑		
TAR14						镀蓝白锌		
TAR15						镀镍		
TAR18						银灰色达克罗		
TAR01						发黑		
TAR04			镀镍					
TAR19			10.9	10B21	37~42HRC	—	银灰色达克罗	
TAR06							40Cr	
TAR02							12.9	SCM435
TAR05							A2-70	SUS304
TAR05	A4-70	SUS316						



适用标准: ISO 7380-1-2011
JIS B 1174-2006
GB/T 70.2-2008

视角标准: 第一视角

强度等级8.8

代码	M	L	P 螺距	D		K		S		h (min)	d	a
				max	min	max	min	max	min			
(10B21)	3	4 5 6 8 10 12 14 16 18 20	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
TAR12	4	5 6 8 10 12 14 16 18 20	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
TAR14	5	6 8 10 12 14 16 18 20 25	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
TAR15	6	8 10 12 14 16 18 20 25 30	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
(35K)	8	10 12 14 16 18 20 25 30	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
TAR18	10	12 14 16 18 20 25 30	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3
	12	14 16 18 20 25 30	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5

强度等级10.9

代码	M	L	P 螺距	D		K		S		h (min)	d	a
				max	min	max	min	max	min			
10B21 (发黑) TAR01	2	4 5 6 8 10 12 16 20	0.4	3.5	3.3	1.3	1.16	1.36	1.32	0.6	2.5	0.8
	2.5	4 5 6 8 10 12 16 20 30	0.45	4.7	4.5	1.5	1.36	1.56	1.52	0.8	2.5	0.6
	3	4 6 8 10 12 14 16 18 20 25 30 35 40 45 50	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
	4	6 8 10 12 16 20 25 30 35 40 45 50	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
	5	6 8 10 12 14 16 20 25 30 35 40 45 50	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
	6	8 10 12 14 16 20 25 30 35 40 45 50 55 60	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
	8	10 12 16 20 25 30 35 40 45 50 55 60 65 70 75 80 85 90 100	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
10B21 (镀镍) TAR04	4	6 8 10 12 14 16 18 20 25 30 35 40 45 50	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3
	5	6 8 10 12 14 16 20 25 30 35 40 45 50	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5
	6	8 10 12 14 16 20 25 30 35 40 45 50 55 60 65 70	2	28	27.48	8.8	8.44	10.175	10.025	5.2	18.2	3.5
	8	10 12 16 20 25 30 35 40 45 50 55 60 65 70 75 80 90 100	2.5	35	34.5	11.15	10.7	13.225	13.075	6.35	22.2	3.5
	10	12 14 16 18 20 22 24 26 28 30 32 34 36 38 40 42 44 46 48 50 52 54 56 58 60 62 64 66 68 70 72 74 76 78 80 82 84 86 88 90 92 94 96 98 100	3	42	41.5	13.45	13.05	15.625	15.475	7.625	25.2	3.5
	12	14 16 18 20 22 24 26 28 30 32 34 36 38 40 42 44 46 48 50 52 54 56 58 60 62 64 66 68 70 72 74 76 78 80 82 84 86 88 90 92 94 96 98 100	3.5	48	47.5	15.15	14.75	17.725	17.575	8.875	29.2	3.5
	16	16 18 20 22 24 26 28 30 32 34 36 38 40 42 44 46 48 50 52 54 56 58 60 62 64 66 68 70 72 74 76 78 80 82 84 86 88 90 92 94 96 98 100	4	56	55.5	18.15	17.75	21.225	21.075	10.625	35.2	3.5

强度等级10.9/12.9

代码	M	L	P 螺距	D		K		S		h (min)	d	a
				max	min	max	min	max	min			
强度等级10.9 (40Cr) TAR19	3	4 5 6 8 10 12 14 16 18 20	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
	4	5 6 8 10 12 14 16 18 20	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
	5	6 8 10 12 14 16 18 20 25	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
	6	8 10 12 14 16 18 20 25 30 35 40 45 50	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
强度等级12.9 (SCM435) TAR06	8	10 12 14 16 18 20 25 30	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
	10	16 18 20 25 30	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3
	12	16 20 25 30	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5

强度等级A2-70

代码	M	L	P 螺距	D		K		S		h (min)	d	a
				max	min	max	min	max	min			
(SUS304) TAR02	2.5	3 4 5 6 8 10 12 16 18 20 25	0.45	4.7	4.5	1.5	1.36	1.56	1.52	0.8	2.5	0.6
	3	4 6 8 10 12 14 16 18 20 25 30 35 40 45 50	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
	4	6 8 10 12 14 16 18 20 25 30 35 40 45 50 55 60 65 70 75	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
	5	6 8 10 12 14 15 16 18 20 25 30 35 40 45 50 55 60 65 70 75 80 85 90 100	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
	6	8 10 12 14 15 16 18 20 25 30 35 40 45 50 55 60 65 70 75 80 85 90 100	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
	8	12 14 16 18 20 25 30 35 40 45 50 55 60 65 70 75 80 85 90 100	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
	10	16 18 20 22 25 30 35 40 45 50 55 60 65 70 75 80 85 90 100	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3
12	20 25 30 35 40 45 50 55 60 65 70 75 80 85 90 100	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5	

强度等级A4-70

代码	M	L	P 螺距	D		K		S		h (min)	d	a
				max	min	max	min	max	min			
(SUS316) TAR05	3	6 8 10 12 18 35	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
	4	6 8 10 12 14 16 20 25 30 35 40 55 65 75	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
	5	10 12 16 20 25 30 35 40 45 50 55 65 70	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
	6	10 12 16 20 25 30 35 40 45 50	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
	8	12 16 20 25 30 35 40 45 50	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
	10	16 20 25 30 35 40 45 50 60 70 80	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3
12	25 30 35 40	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5	



请按图示订货

型号	M	L
代码	3	4 6 8 10 12
	4	6 8 10 12

TAR01—M4—L12



未税价(元)

● 优惠价
数量 1~49 50~
价格 100% 另行报价



交货期
5