


内六角平圆头螺钉

代码	类型	螺纹	强度等级	材质	硬度	表面处理
TAR12	内六角平圆头螺钉	粗牙	8.8	10B21	—	发黑
TAR14						镀蓝白锌
TAR15				35K		镀镍
TAR18						银灰色达克罗
TAR01			10.9	10B21	37~42HRC	发黑
TAR04						镀镍
TAR19				40Cr		银灰色达克罗
TAR06						
TAR02			12.9	SCM435		
TAR05			A2-70	SUS304		
			A4-70	SUS316		



① 适用标准: ISO 7380-1-2011
JIS B 1174-2006
GB/T 70.2-2008



强度等级8.8

型号		L										P	D		K		S		h	d	a
代码	M											螺距	max	min	max	min	max	min	(min)		
(10B21)	3	4	5	6	8	10	12	14	16	18	20	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
	4	5	6	8	10	12	14	16	18	20	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4	
	5	6	8	10	12	14	16	18	20	25	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6	
	6	8	10	12	14	16	18	20	25	30	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2	
(35K)	8	10	12	14	16	18	20	25	30	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5		
	10	12	14	16	18	20	25	30	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3			
	12	14	16	18	20	25	30	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5				

强度等级10.9

型号		L														P	D			K		S		h	d	a				
代码	M															螺距	max	min	max	min	max	min	(min)							
10B21 (发黑) TAR01	2	4	5	6	8	10	12	16	20						0.4	3.5	3.3	1.3	1.16	1.36	1.32	0.6	2.5	0.8						
	2.5	4	5	6	8	10	12	16	20	30					0.45	4.7	4.5	1.5	1.36	1.56	1.52	0.8	2.5	0.6						
	3	4	6	8	10	12	14	16	18	20	25	30	35	40	45	50	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1				
	4	6	8	10	12	16	20	25	30	35	40	45	50				0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4				
	5	6	8	10	12	14	16	20	25	30	35	40	45	50				0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6			
	6	8	10	12	14	16	20	25	30	35	40	45	50	55	60				1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2		
	8	10	12	16	20	25	30	35	40	45	50	55	60	65	70	75	80	85	90	100	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
	10	12	16	20	25	30	35	40	45	50	55	60	65	70	75	80	90	100				1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2
12	16	20	25	30	35	40	45	50	55	60	65	70	75	80	90	100				1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5	
16	20	25	30	35	40	45	50	55	60	65	70	75	80	90	100				2	28	27.48	8.8	8.44	10.175	10.025	5.2	18.2	4		
10B21 (镀镍) TAR04	3	4	6	8	10	12	16	20	25	30	35	40	45	50				0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1			
	4	6	8	10	12	14	16	18	20	25	30	35	40	45	50				0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4		
	5	6	8	10	12	14	16	20	25	30	35	40	45	50				0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6			
	6	8	10	12	16	18	20	25	30	35	40	45	50	55	60	65	70				1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
	8	10	12	16	20	25	30	35	40	45	50	55	60	70	80	85	90				1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5
	10	12	16	20	25	30	35	40	45	50	55	60							1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3		
	12	14	16	18	20	25	30													1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5	
	16	20	25	30																2	28	27.48	8.8	8.44	10.175	10.025	5.2	18.2	4	

强度等级10.9/12.9

型号		L										P	D		K		S		h	d	a
代码	M											螺距	max	min	max	min	max	min	(min)		
强度等级 10.9 (40Cr) TAR19	3	4	5	6	8	10	12	14	16	18	20	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1
	4	5	6	8	10	12	14	16	18	20		0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
	5	6	8	10	12	14	16	18	20	25		0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
	6	8	10	12	14	16	18	20	25	30		1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
强度等级 12.9 (SCM435) TAR06	8	10	12	14	16	18	20	25	30		1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5	
	10	12	14	16	18	20	25	30		1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3		
	12	14	16	18	20	25	30		1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5			

强度等级A2-70

型号		L											P	D		K		S		h	d	a													
代码	M												螺距	max	min	max	min	max	min	(min)															
(SUS304) TAR02	2.5	3	4	5	6	8	10	12	16	18	20	25	0.45	4.7	4.5	1.5	1.36	1.56	1.52	0.8	2.5	0.6													
	3	4	6	8	10	12	14	16	18	20	25	30	35	40	45	50	0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1									
	4	6	8	10	12	14	16	18	20	25	30	35	40	45	50	55	60	65	70	75	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4					
	5	6	8	10	12	14	15	16	18	20	25	30	35	40	45	50	55	60	65	70	75	80	85	90	100	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6
	6	8	10	12	14	15	16	18	20	25	30	35	40	45	50	55	60	65	70	75	80	85	90	100	1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2	
	8	10	12	14	16	18	20	25	30	35	40	45	50	55	60	65	70	75	80	85	90	100	1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5			
	10	12	14	16	18	20	22	25	30	35	40	45	50	55	60	65	70	75	80	85	90	100	1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2	3			
12	14	16	18	20	25	30	35	40	45	50	55	60	65	70	75	80	85	90	100	1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5						

强度等级A4-70

型号		L										P	D		K		S		h	d	a				
代码	M											螺距	max	min	max	min	max	min	(min)						
(SUS316) TAR05	3	6	8	10	12	18	35					0.5	5.7	5.4	1.65	1.4	2.08	2.02	1.04	3.6	1				
	4	6	8	10	12	14	16	20	25	30	35	40	55	65	75	0.7	7.6	7.24	2.2	1.95	2.58	2.52	1.3	4.7	1.4
	5	10	12	16	20	25	30	35	40	45	50	55	65	70	0.8	9.5	9.14	2.75	2.5	3.08	3.02	1.56	5.7	1.6	
	6	10	12	16	20	25	30	35	40	45	50					1	10.5	10.07	3.3	3	4.095	4.02	2.08	6.8	2
	8	12	16	20	25	30	35	40	45	50					1.25	14	13.57	4.4	4.1	5.14	5.02	2.6	9.2	2.5	
	10	16	20	25	30	35	40	45	50	60	70	80					1.5	17.5	17.07	5.5	5.2	6.14	6.02	3.12	11.2
	12					25	30	35	40					1.75	21	20.48	6.6	6.24	8.175	8.025	4.16	14.2	3.5		

