





方型 ▶ 磁铁

代码	类型	磁力方向	材质	表面处理	耐热温度
BLS61	方型	轴向	钕磁铁	镀镍	80°C
BLS62			铁氧体磁铁	—	300°C



磁力方向：轴向



视角标准：第一视角

型号		A公差	B	B公差	T	T公差	吸引力 N(kgf)	表面磁通密度 高斯(G)
代码	A							
BLS61	3		3		5		2.8(0.29)	4000~4300
	4		4				5.6(0.57)	4200~4500
	5		5		5		8.9(0.91)	4300~4600
	6		6		6		13.7(1.4)	4400~4700
	8		8		6		23.2(2.37)	4300~4600
					8			
					1		2.7(0.28)	1600~1900
			5		2		8.5(0.87)	2900~3200
					5			4200~4400
					8		16.8(1.71)	4100~4400
	10				1		6.5(0.66)	1700~2000
					2		11.8(1.2)	1700~2700
			10		3		6.5(0.66)	1700~2000
					5		11.8(1.2)	2400~2700
		0 -0.1		0 -0.1	8		39.3(4.01)	4400~4700
					10	-0.1		
					3		13.9(1.42)	3000~3300
			5		5		23.7(2.42)	4000~4300
	15				10		31.1(3.2)	4600~4900
					3		23.9(2.44)	2800~3100
			10		5		34.3(3.5)	3200~3700
					10		61.4(6.27)	4500~4800
			5		10		40.8(4.16)	4500~4800
	20				5		47.7(4.87)	3400~3700
			10		10		77.8(7.94)	4600~4900
					5			
			15		6		69.7(7.11)	3200~3700
			20		5		84.8(8.65)	3000~3300
	30						95.6(9.75)	3000~3400
			30		6		110.8(11.31)	3200~3700

① 吸引力、表面磁通密度是指磁铁单件的值(仅供参考)。

型号		A公差	B	B公差	T	T公差	吸引力 N(kgf)	表面磁通密度 高斯(G)
代码	A							
BLS62	10	±0.1	5	±0.1			1.6(0.16)	900~1100
	20		10				4.9(0.50)	950~1150
	30	±0.15	20	±0.15	5		9.8(1.00)	
	50	±1.2	20	±0.4			12.8(1.30)	1050~1250
						±0.1		
	30	±0.15	30	±0.15			21.6(2.20)	
		±0.6	60	±1.2	10		29.5(3.00)	1150~1450
	40	±0.8	20	±0.4			17.7(1.80)	
			40	±0.8			31.3(3.20)	

① 吸引力、表面磁通密度是指磁铁单件的值(仅供参考)。



请按图示订货

型号		B	T
代码	A		
BLS61	3	3	5
	4	4	5

BLS61 — A3 — B3 — T5



未税价(元)

优惠价
数量 1~49 50~
价格 100% 另行报价

① BLS61



未税价(元)

优惠价
数量 1~9 10~
价格 100% 另行报价

① BLS62



交货期
1